



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : H05B 33/00, 33/12	A1	(11) International Publication Number: WO 00/65879 (43) International Publication Date: 2 November 2000 (02.11.00)
(21) International Application Number: PCT/US00/11161 (22) International Filing Date: 27 April 2000 (27.04.00) (30) Priority Data: 60/131,475 28 April 1999 (28.04.99) US (71) Applicant: eMAGIN CORPORATION [US/US]; Hudson Valley Research Park, 2070 Route 52, Hopewell Junction, NY 12533 (US). (72) Inventors: PRANDO, Gregory, T.; 705 Hudson Harbour Drive, Poughkeepsie, NY 12601 (US). CAMPOS, Richard, A.; 4 Perry Street, Cortlandt Manor, NY 10567 (US). TICE, Kerry, O.; 2 White Oaks Road, Hyde Park, NY 12538 (US). (74) Agents: COYNE, Patrick, J. et al.; Collier Shannon Scott, PLLC, Suite 400, 3050 K Street, N.W., Washington, DC 20007 (US).		(81) Designated States: European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: ORGANIC ELECTROLUMINESCENCE DEVICE WITH HIGH EFFICIENCY REFLECTING ELEMENT <div data-bbox="269 1165 1336 1474" data-label="Diagram"> </div> (57) Abstract <p>The present invention is direct to the concept of an electrode for an OLED (20) formed from multiple layers of metal and dielectric materials that can be ordered to produce a highly efficient electrode (22). The layers of the electrode (22) may be stacked such that different portions of the electrode fulfill the separate functionalities of high electrical conductivity, high electrical injection and high optical transmission/reflection.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

ORGANIC ELECTROLUMINESCENCE DEVICE WITH HIGH EFFICIENCY REFLECTING ELEMENT

CROSS REFERENCE TO RELATED PATENT APPLICATION

This application relates to and claims priority on provisional application serial number 60/131,475, filed April 28, 1999.

FIELD OF INVENTION

5 The present invention relates to an organic electroluminescence device. In particular, the present invention relates to a layered or stacked electrode for an organic electroluminescence.

BACKGROUND OF THE INVENTION

10 An organic electroluminescence device or organic light emitting device ("OLED") is a stack of organic thin films which are in physical contact between two electrodes. The basic structure of an OLED 1 is illustrated in Fig. 1. The OLED 1 includes a substrate 10, a first electrode 11 formed on the substrate 10, at least one organic thin film layer 12 formed on the first electrode 11, and a second electrode 13 formed on the at least one organic thin film layer 12. Typically, several organic thin film layers are sandwiched between the electrodes 11 and 13. The electrodes 11 and 13 may be optically reflective or transmissive, depending on the desired direction of light exiting from the OLED 1. The OLED 1 may be encapsulated to maintain material and structural integrity.

15 The first electrode 11 may be formed from indium tin oxide ("ITO") which has high optical transmission, electrical conductivity and high electrical injection into the at least one organic thin film layer 12. An electrode formed from ITO can be made to have 80-90% optical transmission with 10-100% sheet resistances. ITO is also an operationally good positive-carrier for electrical injection into the at least one organic thin film layer 12. When the first electrode 11 is formed from ITO on substrate 10, the OLED 1 is known as a "down emitting" because the optical output passes through the substrate 10 to the viewer. The second electrode 13 is then formed from a partially reflective material (e.g., molybdenum, ruthenium and vanadium). The second electrode 13 has a thickness of approximately 1000Å.

In a "down emitting" OLED, the second electrode **13** may be formed from a pair of layers **131** and **132**, as shown in Fig. 2. A very thin layer **131** of a dielectric material (e.g., LiF and SiO₂) is formed on the at least one thin film layer **12**. The layer **131** has a thickness of less than 100Å. A thicker layer **132** of aluminum is formed on the thin layer **131**. The thicker layer **132** of aluminum has an approximate thickness of 2000Å. Although the operation of composite electrode having layers **131** and **132** is not fully understood, the thin layer **131** is thought to assist electron injection into select organic materials of the thin film layer **12**. The aluminum layer **132** is believed to provide functional conductivity and reflectivity within the context of a "down emitting" OLED.

OBJECTS OF THE INVENTION

It is an object of the present invention to increase the optical output efficiency of an organic electroluminescence device.

It is another object of the present invention to provide an OLED having an electrode having high optical transmission.

It is another object of the present invention to provide an OLED having an electrode having high optical reflection.

It is another object of the present invention to provide an OLED having an electrode having high electrical conductivity.

It is another object of the present invention to provide an OLED having a low-loss, highly directional and reflective element as an integral part of a composite electrode element.

It is another object of the present invention to provide an OLED having a low-loss, highly directional and reflective element as an integral part of a composite electrode element that contacts the organic stack of the OLED.

It is another object of the present invention to provide an OLED having omnidirectional reflectors as part of an electrode element to boost performance of the OLED.

It is another object of the present invention to provide an OLED having omnidirectional reflectors as part of an electrode element to boost performance of the OLED by promoting greater optical output through the reduction of optical losses.

It is another object of the present invention to provide an OLED having omnidirectional reflectors as part of an electrode element to boost performance of the OLED by promoting greater directionality of the output optical beam.

It is another object of the present invention to provide an OLED having an electrode comprising a layered stack of metallic and/or dielectric materials.

It is another object of the present invention to provide an OLED having an electrode comprising a layered stack of metallic and/or dielectric materials, which separately functionalize the requirements of high optical transmission or reflection, high electrical conductivity, and high electrical injection into the organic stack.

SUMMARY OF THE INVENTION

The present invention is directed to the concept of an electrode for an OLED formed from multiple layers of metal and dielectric materials that can be ordered to produce a highly efficient electrode. The layers of the electrode may be stacked such that different portions of the electrode fulfill the separate functionalities of (1) high electrical conductivity, (2) high electrical injection and (3) high optical transmission/reflection.

The present invention is directed to an OLED having a substrate, a first electrode formed on said substrate, at least one organic thin film layer formed on the first electrode, and a second electrode formed on the at least one organic thin film layer. In accordance with the present invention, at least one of the first and second electrodes includes a plurality of electrode layers. The plurality of electrode layers includes a thin film layer formed at least one of a metal and an oxide, and a multilayer reflector. The thin film layer preferably has a thickness of less than 100Å.

The multilayer reflector includes a plurality of layers. The plurality of layers may include at least one metal layer and at least one dielectric material layer. The plurality of layers preferably includes alternating layers of the at least one metal layer and the at least one dielectric material layer.

In accordance with one embodiment of the present invention, the first electrode includes the plurality of electrode layers. In accordance with another embodiment of the present invention, the second electrode includes the plurality of electrode layers.

The plurality of electrode layers preferably includes at least one layer formed from a high electrical conductivity material. The plurality of electrode layers preferably includes at least one layer formed from a high electrical injection material. The plurality of electrode layers preferably includes at least one layer formed from a material having a high optical transmission. The plurality of electrode layers preferably includes at least one layer formed from a material having a high optical reflection.

The present invention is also directed to an electrode for an OLED, the electrode includes a plurality of electrode layers, wherein the plurality of electrode layers includes a thin film layer formed at least one of a metal and an oxide, and a multilayer reflector. The thin film layer has a thickness of less than 100Å. The multilayer reflector includes a plurality of layers. The plurality of layers includes at least one metal layer and at least one dielectric material layer. The plurality of layers preferably includes alternating layers of the at least one metal layer and the at least one dielectric material layer.

BRIEF DESCRIPTION OF THE DRAWINGS

The invention will now be described in conjunction with the following drawings in which like reference numerals designate like elements and wherein:

Fig. 1 is a schematic view of a conventional OLED;

Fig. 2 is a schematic view of another conventional OLED;

Fig. 3 is a schematic view of an upwardly emitting OLED according to an embodiment of the present invention; and

Fig. 4 is a schematic view of a downwardly emitting OLED according to another embodiment of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

Reference will now be made in detail to a preferred embodiment of the present invention, an example of which is illustrated in the accompanying drawings. The OLED

in accordance with one embodiment of the present invention is illustrated in Fig. 3. The OLED **20** includes a substrate **21**. A first electrode **22** is formed on the substrate **21**. At least one organic thin film layer **23** is formed on the first electrode **22**. A second electrode **24** is formed on the at least one organic thin film layer **23**. The OLED **20** is an upwardly emitting OLED. In an upwardly emitting OLED, light is transmitted through the second electrode **24**. The substrate **21** is formed from an opaque material (e.g., silicon). The second electrode **24** is formed from a suitable light transmissive material to permit output of the OLED to exit away from the substrate **21** in the direction of the arrows illustrated in Fig. 3.

The first electrode **22** is formed from a plurality of layers. A thin film layer **221** is in direct contact with the at least one organic thin film layer **23**. The layer **221** has a thickness of less than 100Å. The layer **221** is formed from a material that promotes positive carrier injection into the at least one organic thin film layer **23**. The layer **221** is preferably formed from a metal or an oxide. Suitable metals include molybdenum, ruthenium and vanadium. The present invention, however, is not limited to these materials, rather metals exhibiting similar physical properties are considered to be well within the scope of the present invention. The layer **221** may be formed from oxides of molybdenum, ruthenium, and vanadium or other suitable metals. ITO, aluminum-zinc oxide and mixtures thereof are suitable materials for layer **221**.

Positioned between the substrate **21** and the thin layer **221** are alternating layers of metals and dielectric materials **222**, **223**, **224**, **225** forming a high-performance, multilayer reflector **220**. This reflector layer **220** has ideal reflectivities, omnidirectionality and low loss, in what is known as a "dielectric omnidirectional reflector." This composite reflector is tuned to the wavelength of electroluminescence emission by suitable choices of the alternating metal and dielectric materials. The omnidirectional mirror combines the best properties of each by inhibiting energy losses through optical interference effects in the periodic, alternating structure.

A second embodiment of the present invention depicted a "downwardly emitting" OLED **30** is illustrated in Fig. 4 having a substrate **31**. In a "down-emitting" application, the

first electrode **32** is of the usual type, e.g., ITO, and the second electrode **34** is reflective. A thin layer **341** is positioned adjacent to the at least one organic layer **33**. The layer **341** is a thin, transparent negative-carrier injector having a thickness of less than 100Å. The layer **341** is preferably formed from codeposited layer of magnesium and silver.

5 A plurality of alternating layer **342**, **343**, **344** and **345** forming a high-performance, multilayer reflector **340** are formed on thin layer **341**. The multilayer reflector **340** may also serve as a protective layer for the thin metallic injector **341**.

10 While this invention has been described in conjunction with specific embodiments thereof, it is evident that many alternatives, modifications and variations will be apparent to those skilled in the art. Accordingly, the preferred embodiments of the invention as set forth herein are intended to be illustrative, not limiting. Various changes may be made without departing from the spirit and scope of the invention as defined in the following claims.

What is claimed is:

1. An organic light emitting device comprising:
a substrate;
a first electrode formed on said substrate;
at least one organic thin film layer formed on said first electrode; and
5 a second electrode formed on said at least one organic thin film layer, wherein at least one of said first and second electrodes includes a plurality of electrode layers.
2. The organic light emitting device according to Claim 1, wherein said plurality of electrode layers comprises:
a thin film layer formed of at least one of a metal and an oxide; and
a multilayer reflector.
3. The organic light emitting device according to Claim 2, wherein said thin film layer has a thickness of less than 100Å.
4. The organic light emitting device according to Claim 2, wherein said multilayer reflector includes a plurality of layers.
5. The organic light emitting device according to Claim 4, wherein said plurality of layers includes at least one metal layer and at least one dielectric material layer.
6. The organic light emitting device according to Claim 5, wherein said plurality of layers includes alternating layers of said at least one metal layer and said at least one dielectric material layer.
7. The organic light emitting device according to Claim 2, wherein said first electrode includes said plurality of electrode layers.
8. The organic light emitting device according to Claim 2, wherein said second electrode includes said plurality of electrode layers.
9. The organic light emitting device according to Claim 1, wherein said plurality of electrode layers includes at least one layer formed from a high electrical conductivity material.
10. The organic light emitting device according to Claim 1, wherein said plurality of electrode layers includes at least one layer formed from a high electrical injection material.

11. The organic light emitting device according to Claim 1, wherein said plurality of electrode layers includes at least one layer formed from a material having a high optical transmission.

12. The organic light emitting device according to Claim 1, wherein said plurality of electrode layers includes at least one layer formed from a material having a high optical reflection.

13. An electrode for an organic light emitting device, said electrode comprising:
a plurality of electrode layers, wherein said plurality of electrode layers includes a thin film layer formed at least one of a metal and an oxide, and a multilayer reflector.





14. The electrode according to Claim 13, wherein said thin film layer has a thickness of less than 100Å.

15. The electrode according to Claim 13, wherein said multilayer reflector includes a plurality of layers.

16. The electrode according to Claim 15, wherein said plurality of layers includes at least one metal layer and at least one dielectric material layer.

17. The electrode according to Claim 16, wherein said plurality of layers includes alternating layers of said at least one metal layer and said at least one dielectric material layer.

1/1

**FIG. 1****FIG. 2****FIG. 3****FIG. 4**

INTERNATIONAL SEARCH REPORT

International application No.
PCT/US00/11161

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : H05B 33/00, 33/12

US CL : 313/504, 428/690

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 428/690; 313/498, 499, 500, 501, 502, 503, 504, 505, 506; 315/169.3; 445/35, 46

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
EAST, WEST

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,814,416 A (DODABALAPUR et al) 29 September 1998 (29-09-1998), col. 3, line 54-col. 5, line 6.	1-17
Y	US 5,811,833 A (THOMPSON) 22 September 1998 (22-09-1998), col. 10, line 26-col 11, line 25.	1-17
Y	US 5,674,636 A (DODABALAPUR et al) 07 October 1997 (07-10-1997), entire document.	1-17
Y	US 5,635,307 A (TAKEUCHI et al) 03 June 1997 (03-06-1997), entire document.	1-17
Y	US 5,405,710 A (DODABALAPUR et al) 11 April 1995 (11-04-1995), entire document.	1-17

☐

Further documents are listed in the continuation of Box C.

☐

See patent family annex.

* Special categories of cited documents:	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"A" document defining the general state of the art which is not considered to be of particular relevance	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"E" earlier document published on or after the international filing date	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"&" document member of the same patent family
"O" document referring to an oral disclosure, use, exhibition or other means	
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

21 JUNE 2000

Date of mailing of the international search report

28 JUL 2000

Name and mailing address of the ISA/US
Commissioner of Patents and Trademarks
Box PCT
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

MATTHEW GERIKE

Telephone No. (703) 305-4900